

## ABSTRACT OF THE DISCLOSURE

A precipitated silica with the following physicochemi-

cal properties:

---

	BET surface area	35 to 350 m <sup>2</sup> /g
	BET/CTAB surface area ratio	0.8 to 1.1
5	Pore volume, PV	1.6 to 3.4 ml/g
	Silanol group density (V <sub>2</sub> =	6 to 20 ml
	NaOH consumption)	
	Average aggregate size	250 to 1500 nm
10	CTAB surface area	30 to 350 m <sup>2</sup> /g
	DBP value	150 to 300 ml/100 g
	V <sub>2</sub> /V <sub>1</sub> by Hg porosimetry	0.19 to 0.46
	DBP/CTAB	1.2 to 2.4.

---

is produced by reacting alkali silicate with mineral acids  
 at temperatures of 60 to 95°C while maintaining a pH of 7.5  
 15 to 10.5 and continuously stirring, continuing the reaction  
 to a solids concentration in the precipitation suspension of  
 90 to 120 g/l, adjusting the pH value to a value of less  
 than or equal to 5, filtering out, washing, drying and op-  
 20 tionally grinding or granulating the precipitated silica.  
 The precipitated silica is used as a filler in vulcanizable  
 rubber compounds and vulcanizates.

25

30